



MULTI-PURPOSE PRIMER 067

Features

- Strong adhesion to interior and exterior substrates
- Provides a mildew resistant coating
- Quick drying – 1 hour recoat

Recommended For

Interior: Use on new or previously painted wood, plywood, drywall, ceiling tile, Formica®, Masonite®, ceramic tile, cured plaster, and wall coverings.

Exterior: Use on new or previously painted wood, aluminum, hardboard and vinyl siding, shingles, shakes, concrete, masonry, brick, and non-ferrous metal surfaces. On hard, non-porous surfaces, such as glazed ceramics and non-ferrous metal, **maximum adhesion and hardness** may take 3-4 days to develop.

General Description

A 100% acrylic, interior and exterior primer for all project needs. It combines all the qualities desired in a multi-purpose primer: strong adhesion for all surfaces, provides a mildew-resistant coating and quick drying. Formulated to suppress most light stains.

Limitations

- Not recommended for sealing knots or over pine sap.
- Apply when surface and ambient temperature is above 4.4 °C (40 °F) and below 32.2 °C (90 °F)
- Not recommended for use on floor surfaces.

Product Information		Technical data	
Standard Colours	White (00)	Vehicle Type	100% Acrylic
Tint Bases	NA	Pigment Type	Titanium Dioxide
Colorant System	Up to 60 mL of Gennex® Waterborne Colorants	Volume Solids	36 ± 2%
Certifications & Qualifications:		Coverage per 3.79 L at	32.6 – 41.8 sq. m.
VOC compliant in all regulated areas		Recommended Film Thickness	(350 – 450 sq. ft.)
Eligible for LEED® v4 Credit		Recommended Film Thickness	– Wet 90.5 – 116.4 µm
CDPH v1 Emission Certified		Thickness	(3.6 – 4.6 mils)
Eligible for CHPS low emitting credit		– Dry	32.6 – 41.9 µm
(Collaborative for High Performance Schools)			(1.3 – 1.6 mils)
Master Painters Institute MPI # 6, 39, 137, 137 X-Green™		Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.	
Class A (0-25) over non-combustible surfaces when tested in accordance with ASTM E-84		Dry Time @ 25 °C	– To Touch 30 Minutes
Water Vapor Transmission: ASTM D1653 (method A): 7 perms		(77 °F) @ 50 % RH	– To Recoat 1 Hour
Technical Assistance		High humidity and cool temperatures will result in longer dry, recoat and service times.	
Available in the UK through Benjamin Moore UK showrooms and Authorized Stockists.		Dries By	Evaporation, Coalescence
See www.benjaminmoorepaint.co.uk/stores for contact information.		Viscosity	98 ± 5 KU
Benjamin Moore corporate customer service +1 855-724-6802 or info@benjaminmoore.com		Flash Point	None
		Gloss / Sheen	Flat (5 – 10 @ 85°)
		Surface Temperature at Application	– Min. 4.4 °C (40 °F)
			– Max. 32.2 °C (90 °F)
		Thin With	Do Not Thin
		Clean Up Thinner	Clean Water
		Weight Per 3.79 L	4.5 kg (10.3 lbs.)
		Storage Temperature	– Min. 4.4 °C (40 °F)
			– Max. 32.2 °C (90 °F)
Volatile Organic Compounds (VOC)			
EU Limit for this product is (Cat. A/g) 30 g/L MAX VOC 18 g/L			

Multi-Purpose Primer (067)

Surface Preparation

Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water soluble materials, and mildew. Remove any peeling or scaling paint and sand these areas to feather edges smooth with adjacent surfaces. Glossy areas should be dulled. Drywall surfaces must be free of sanding dust.

New plaster or masonry surfaces must be allowed to cure before applying base coat. Cured plaster should be hard, have a slight sheen and maximum PH of 10; soft, porous or powdery plaster indicates improper cure. Never sand a plaster surface; knife off any protrusions and prime plaster before and after applying patching compound. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles before priming. Wood substrates must be thoroughly dry. Caution: Smooth planed clapboards or siding must be sanded thoroughly to break the "mill glaze" allowing proper penetration and adhesion.

Difficult Substrates: If the surfaces to be painted exhibit severe tannin or smoke staining, an alkyd-based Benjamin Moore primer may be your best choice for conquering these severe conditions. Consult your Benjamin Moore retailer for further guidance.

Primer/Finish Systems

New surfaces should be fully primed, and previously painted surfaces may be primed or spot primed as necessary. For best hiding results use Multi-Purpose Primer tinted to the approximate finish coat colour.

Wood, and engineered wood products

Primer: Multi-Purpose Primer (067)

Bleeding type woods, (cedar and redwood)

Primer: Fresh Start® High-Hiding or Multi-Purpose Primer (067)

Finish: 1 or 2 coats of the appropriate Benjamin Moore® finish coat

Drywall

Primer: Multi-Purpose Primer (067)

Finish: 1 or 2 coats of the appropriate Benjamin Moore® finish coat

Plaster

Primer: Multi-Purpose Primer (067)

Finish: 1 or 2 coats of the appropriate Benjamin Moore® finish coat

Masonry; Rough or Pitted

Primer: Ultra Spec® Masonry Interior/Exterior Hi-Build Block Filler (571)

Finish: 1 or 2 coats of the appropriate Benjamin Moore® finish coat

Masonry; Smooth Poured or Pre-cast Concrete

Primer: Multi-Purpose Primer (067) or Ultra Spec® Masonry Interior / Exterior 100% Acrylic Masonry Sealer (608)

Finish: 1 or 2 coats of the appropriate Benjamin Moore® finish coat

Ferrous Metal (Steel and Iron)

Primer: Super Spec HP® Alkyd Metal Primer (P06)

Finish: 1 or 2 coats of the appropriate Benjamin Moore® finish coat.

Non-Ferrous Metal (galvanized & aluminum)

All new metal surfaces must be thoroughly cleaned with Oil & Grease Emulsifier Corotech® V600 to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion.

Primer: Multi-Purpose Primer (067)

Finish: 1 or 2 coats of the appropriate Benjamin Moore® finish coat

Repaint, All Substrates: Prime bare areas with the primer recommended for the substrate above.

Application

Stir thoroughly before use. Apply one or two coats. For best results, use a Benjamin Moore® Professional custom-blended nylon/polyester brush, Benjamin Moore® Professional roller, or a similar product. This product can also be sprayed.

Brush: Nylon / Polyester

Roller: 10 mm Roller Cover

Spray, Airless

Pressure: 1,500-2,500 psi; Tip: 0.013-0.017

Thinning/Clean Up

Clean Up: Wash painting tools in warm soapy water immediately after use. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

WARNING Contains 2-Methyl-4-isothiazolin-3-one



Hazard statements

H317 - May cause an allergic skin reaction. H412 - Harmful to aquatic life with long lasting effects.

EUH208 - Contains (1,2-Benzisothiazolin-3-one, 5-Chloro-2-methyl-3(2H)-isothiazolone mixture with 2-methyl-3(2H)-isothiazolone (3:1)). May produce an allergic reaction

Precautionary Statements - EU (§28, 1272/2008)

P101 - If medical advice is needed, have product container or label at hand. P102 - Keep out of reach of children. P261 - Avoid breathing dust/fume/gas/mist/vapors/spray. P280 - Wear eye protection/ face protection. P321 - Specific treatment (see supplemental first aid instructions on this label). P501 - Dispose of contents/container to industrial incineration plant.

PROTECT FROM FREEZING

Refer to Safety Data Sheet for additional health and safety information.