


## PRODUCT DESCRIPTION & USE

**Armstead Trade Durable Matt** provides a tough and durable matt finish that is ideal for high traffic areas. It is wipeable and offers good stain resistance. Suitable for all normal interior wall surfaces.

## KEY BENEFITS

- **Hardwearing, scrubbable matt finish**
- **Good stain resistance**
- **Ideal for high traffic areas**

## PACK SIZES



## COLOUR RANGE

<b>Armstead Trade Exclusive:</b>	147 colours
BS4800:	94 colours
RAL:	37 colours
NCS 1 & 2:	3291 colours

Visit [www.armsteadtrade.co.uk](http://www.armsteadtrade.co.uk)

## FILM PROPERTIES

**Chemical Resistance:** Not recommended.

**Heat Resistance:** Not suitable for use on heated surfaces. eg. radiators.

**Water Resistance:** Resistant to the levels of atmospheric humidity present in normal interior environments and will withstand repeated washing. Suitable for use in kitchens and bathrooms. Not suitable for use on immersed surfaces or where there is heavy and prolonged condensation. Do not use externally.

## COMPOSITION (NOMINAL)

<b>Pigment:</b>	Lightfast Pigments.
<b>Binder:</b>	Acrylic Copolymer Emulsion.
<b>Solvent:</b>	Water.

## VOLUME SOLIDS

41% (nominal) for White, colours will vary.

## SURFACE PREPARATION

Surfaces must be sound, clean, dry and free from all defective or poorly adhering material, dirt, grease and salts. New plaster and masonry must be fully dry before priming.

**Note:** Special precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain harmful lead.

## SYSTEM INFORMATION

Stir thoroughly before use.

On very absorbent surfaces apply a sealing coat of thinned **Armstead Trade Durable Matt**.

The normal finishing process is 2 full coats of **Armstead Trade Durable Matt**, but on previously painted surfaces in good condition, where similar colours are used, 1 coat may be sufficient.

As with other water-based paints, do not use when the temperature is below 10°C.

## PRACTICAL COVERAGE



A guide to the practical coverage which can be achieved under normal conditions is up to 14m<sup>2</sup> / litre.

## APPLICATION



Brush, roller, spray and airless spray.

As with other water-based paints, do not apply in temperatures below 8°C (as recommended by British Standard BS 6150)

## THINNING

### Sealing new/bare surfaces:

Add up to 1 part clean water to 10 parts paint.

### Normal use (not to be exceeded):

Thinning is not usually required.

### Conventional spray application:

Add up to 1 part clean water to 5 parts paint.

### Airless spray application:

Thinning is not usually required.

## SPRAY RECOMMENDATIONS

**Conventional Spray:** Satisfactory through most equipment.

**Airless Spray:** A typical recommendation for airless spray application is a minimum working pressure on paint of 140 kg/cm<sup>2</sup> (2000 lb/sq in) with a spray tip size 0.38mm (15 thou) and a spray tip angle 65°.

## DRYING TIMES (SINGLE COAT, STANDARD THICKNESS)



**Touch Dry:** 1-2 hours\*

**Recoat:** 2-4 hours\*

\*Dependent upon temperature and humidity.

## CLEANING UP



After use, remove as much paint as possible from brushes before cleaning with clean water.

## TRANSPORTATION & STORAGE

Do not use or store in extremes of temperature and protect from frost. To prevent spillage, please store and transport upright.

### VOC

---

EU limit value for this product (cat A/a) : 30g/l (2010). This product contains max. 14g/l VOC.

VOC Content Low 0.30% - 7.99%. VOCs (Volatile Organic Compounds) contribute to atmospheric pollution.

### FURTHER SUPPORT

---

Online: [www.armsteadtrade.co.uk](http://www.armsteadtrade.co.uk)

Email: [armstead.advice@akzonobel.com](mailto:armstead.advice@akzonobel.com)

Phone: 0333-222-70-70

Please visit [www.armsteadtrade.co.uk](http://www.armsteadtrade.co.uk) to download safety sheet SDSAM302



Like us on Facebook



Videos on YouTube



Follow us on Twitter



Let's create together a better future for our planet.  
Find out how at: [www.armsteadtrade.co.uk/pp](http://www.armsteadtrade.co.uk/pp)

AkzoNobel, the AkzoNobel logo, Armstead and Planet Possible are trademarks of the AkzoNobel group © AkzoNobel 2014